AMENDMENT UNDER 37 C.F.R. § 1.116 U.S. Appln. No. 09/661,057 Attorney Docket No. Q60771

## AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

## LISTING OF CLAIMS:

- 1. (canceled).
- 2. (previously presented): The liquid crystal cell substrate as claimed in claim 3, wherein the resin substrate comprises a thermosetting epoxy resin.
- 3. (previously presented): A liquid crystal cell substrate comprising an epoxy resin substrate obtained by flow casting and having been formed from a liquid alicyclic epoxy resin not containing an aromatic group and a solid alicyclic epoxy resin not containing an aromatic group, and, closely adhered on the resin substrate, a gas barrier layer, a crosslinked resin layer and a polarizing layer, said polarizing layer comprising a coating layer, wherein the polarizing layer has a thickness of 5  $\mu$ m or smaller.
  - 4. (canceled).
- 5. (previously presented): The liquid crystal cell substrate as claimed in claim 3, wherein the polarizing layer comprises a dichroic dye having lyotropic liquid crystallinity, a liquid crystal polymer layer containing a dichroic dye, or a lyotropic substance containing a dichroic dye.
- 6. (original): The liquid crystal cell substrate as claimed in claim 2, wherein the polarizing layer comprises a dichroic dye having lyotropic liquid crystallinity, a liquid crystal polymer layer containing a dichroic dye, or a lyotropic substance containing a dichroic dye.

AMENDMENT UNDER 37 C.F.R. § 1.116 U.S. Appln. No. 09/661,057 Attorney Docket No. Q60771

- 7. (previously presented): The liquid crystal cell substrate as claimed in claim 3, wherein the polarizing layer is in contact with one side of the resin substrate or is located between the gas barrier layer and the crosslinked resin layer.
- 8. (original): The liquid crystal cell substrate as claimed in claim 2, wherein the polarizing layer is in contact with one side of the resin substrate or is located between the gas barrier layer and the crosslinked resin layer.

3